

PATENT ABSTRACTS OF JAPAN(11)Publication number : **61-071804**(43)Date of publication of application : **12.04.1986**

(51)Int.Cl.

B01D 13/04(21)Application number : **59-192712**(71)Applicant : **TOYO SODA MFG CO LTD**(22)Date of filing : **17.09.1984**(72)Inventor : **SAITO SHOZABURO
ITAYA KINGO****(54) POROUS ALUMINUM OXIDE MEMBRANE**

(57)Abstract:

PURPOSE: To obtain an Al-membrane for an ultrafiltration membrane rich in solvent resistance and heat resistance and showing sharp fractional capacity, by forming an aluminum oxide layer to the surface of metal aluminum by applying electrolysis to metal aluminum in an anodic oxidizing electrolyte.

CONSTITUTION: As aluminum being a stock material, metal aluminum or an alloy, which consists of aluminum and a metal such as Si, Fe, Mn, Mg, Cu, Zn, Cr, Ni, Ti or Pd, is used in a thickness of several thousand Wseveral Å. This metal aluminum or alloy is used as an anode and electrolyzed in a solution of an electrolyte capable of forming a porous aluminum oxide film such as sulfuric acid, oxalic acid, phosphoric acid or chromic acid. Electrolytic voltage is several W80V. Next, the non-oxidized metal and the aluminum oxide barrier layer are removed by etching according to a proper method to obtain an aluminum oxide ultrafiltration membrane with a thickness of 1W200μm.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]